



POTENSI PERTAMBANGAN



Berbagai Jenis Marmer Amfoang yang telah diproduksi

	Location	: Fatu Feliu, Timor Island
Batu Taupe	Availability	: Excellent
	Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
	Colours	: Pink-Red, Brown, Grey
	Water absorption	: 0.663 %
	LA Abrasion	: 12.99 %
	Compressive Strength	: 466.14 kg / cm ²
	Bending Strength	: 165.37 kg / cm ²
	Modulus of Rupture	: 31.81 kg / cm ²
	Bulk Specific Gravity	: 2.717
	Hardness	: 7 Mohs
	Porosity	: 1.811 %
	Soudness	: 12.99 %
	Resistance	: 0.038 mm / minute

Batu Cream



Tanah Rosa



Oenam Classic Gray



Verde Beige



Bianco Gray



Lelogama Classic Cream



Verde Gray


Location	: Fatumnutu, Timor Island
Availability	: Excellent
Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
Colours	: Creme, Grey, Pink-Red
Water absorption	: 0.315 %
LA Abrasion	: 22.32 %
Compressive Strength	: 820.42 kg / cm ²
Bending Strength	: 820 N
Modulus of Rupture	: 9.23 MPA
Bulk Specific Gravity	: 2.717
Hardness	: 8 Mohs
Porosity	: 0.006 %
Soudness	: 2.14 %
Resistance	: 0.025 mm / minute

Location	: Fatu Nuabena, Timor Island
Availability	: Excellent
Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
Colours	: Combination of Grey, Creme
Water absorption	: 0.344 %
LA Abrasion	: 24.08 %
Compressive Strength	: 816.23 kg / cm ²
Bending Strength	: 670 N
Modulus of Rupture	: 7.54 MPA
Bulk Specific Gravity	: 2.726
Hardness	: 8 Mohs
Porosity	: 0.005 %
Soudness	: 0.90 %
Resistance	: 0.024 mm / minute

Location	: Fatu Nuabena, Timor Island
Availability	: Excellent
Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
Colours	: Combination of Grey, Red, Creme
Water absorption	: 0.299 %
LA Abrasion	: 19.20 %
Compressive Strength	: 912.01 kg / cm ²
Bending Strength	: 700 N
Modulus of Rupture	: 7.88 MPA
Bulk Specific Gravity	: 2.743
Hardness	: 9 Mohs
Porosity	: 0.006 %
Soudness	: 1.79 %
Resistance	: 0.026 mm / minute



Nusa Brown



Nusa Red

Location	: Fatu Feliu, Timor Island
Availability	: Limited
Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
Colours	: Pink-Red, Brown, Grey
Water absorption	: 0.663 %
LA Abrasion	: 12.99 %
Compressive Strength	: 466.14 kg / cm ²
Bending Strength	: 165.37 kg / cm ²
Modulus of Rupture	: 31.81 kg / cm ²
Bulk Specific Gravity	: 2.717
Hardness	: 7 Mohs
Porosity	: 1.811 %
Soudness	: 12.99 %
Resistance	: 0.038 mm / minute



Oenam Taupe Vein



Oenam Mountain

Location	: Fatumnutu, Timor Island
Availability	: Excellent
Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
Colours	: Creme, Grey, Pink-Red
Water absorption	: 0.315 %
LA Abrasion	: 22.32 %
Compressive Strength	: 820.42 kg / cm ²
Bending Strength	: 820 N
Modulus of Rupture	: 9.23 MPA
Bulk Specific Gravity	: 2.717
Hardness	: 8 Mohs
Porosity	: 0.006 %
Soudness	: 2.14 %
Resistance	: 0.025 mm / minute



Rosa Timor



Timor Red

Location	: Fatufeliu, Timor Island
Availability	: Limited
Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
Colours	: Pink-Red, Brown, Grey
Water absorption	: 0.663 %
LA Abrasion	: 12.99 %
Compressive Strength	: 466.14 kg / cm ²
Bending Strength	: 165.37 kg / cm ²
Modulus of Rupture	: 31.81 kg / cm ²
Bulk Specific Gravity	: 2.717
Hardness	: 7 Mohs
Porosity	: 1.811 %
Soudness	: 12.99 %
Resistance	: 0.038 mm / minute



Oenam Classic Cream



Oenam Yellow Cream

Location	: Fatumnutu, Timor Island
Availability	: Excellent
Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
Colours	: Creme, Grey, Pink-Red
Water absorption	: 0.315 %
LA Abrasion	: 22.32 %
Compressive Strength	: 820.42 kg / cm ²
Bending Strength	: 820 N
Modulus of Rupture	: 9.23 MPA
Bulk Specific Gravity	: 2.717
Hardness	: 8 Mohs
Porosity	: 0.006 %
Soudness	: 2.14 %
Resistance	: 0.025 mm / minute



Timor Tanah Gray



Timor Beige

Location	: Fatu Nuabena, Timor Island
Availability	: Excellent
Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
Colours	: Combination of Grey, Creme
Water absorption	: 0.344 %
LA Abrasion	: 24.08 %
Compressive Strength	: 816.23 kg / cm ²
Bending Strength	: 670 N
Modulus of Rupture	: 7.54 MPA
Bulk Specific Gravity	: 2.726
Hardness	: 8 Mohs
Porosity	: 0.005 %
Soudness	: 0.90 %
Resistance	: 0.024 mm / minute



Lelogama Yellow Cream



Lelogama Veined Beige

Location	: Fatu Nuabena, Timor Island
Availability	: Excellent
Block Size Dimension	: 2.80 m x 1.80 m x 1.60 m
Colours	: Combination of Grey, Red, Creme
Water absorption	: 0.299 %
LA Abrasion	: 19.20 %
Compressive Strength	: 912.01 kg / cm ²
Bending Strength	: 700 N
Modulus of Rupture	: 7.88 MPA
Bulk Specific Gravity	: 2.743
Hardness	: 9 Mohs
Porosity	: 0.006 %
Soudness	: 1.79 %
Resistance	: 0.026 mm / minute